





Chamäleon GmbH  
 Rudolf-Diesel-Straße, 8a  
 69115 Heidelberg-Germany  
 Tel.: +49-(0)-6221 520440  
 Fax: +49-(0)-6221 520449  
 E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

### Applications:

	spraying pressure	spraying nozzle	spraying operations
Air/ Flowjar - Spray gun	2 - 2.5 bar	1.2 - 1.4 mm	1 - 2
HVLP	2 - 2.5 bar (nozzle int.pressure 0.7 bar)	1.2 - 1.4 mm	1 - 2

### Drying:

	recoat time	dust dry	set to touch	full hardness
Object temp. 20° C		25 - 30 min.	6 - 8 h	24 h
Object temp. 60° C		5 min.	30 min.	1 h

### Recommendations:

Operation conditions: from + 10 °C and up to 75% relative air humidity.

By BC paints apply a thin film (sticking operation), flash off approx. 3 - 5 min. and then recoat by 1 - 2 normal spraying operations.

Shelf life of at least 3 years, if stored in tightly closed original containers.